

InsuBuild 110T

High range, water reducing superplasticiser for producing free flowing concretes and promoting high early and ultimate strengths.

DESCRIPTION OF PRODUCT

InsuBuild 110T is formulated from synthetic polymers specially designed to grant free flowing qualities to concrete.

A free flowing concrete is a fluid concrete with a slump of at least 200mm, easily flowing, but at the same time free from segregation and having the same w/c ratio as that of a low slump concrete (25mm) without admixture.

InsuBuild 110T is chloride free.

ADVANTAGES

InsuBuild 110T considerably improves the properties of fresh and hardened concrete.

PRIMARY USES

- Microsilica concrete.
- Mass concrete pours.
- Readymixed concrete.
- Longdistance transport.
- Pumpedconcrete.
- Casting in hot climates.

TO OBTAIN

- Reduced thermal peaks.
- High workability for longer periods.
- Lower pumping pressure.
- Delayed setting with longer workability.
- Higher ultimate strengths.
- Reduced permeability.
- Improved durability.

COMPATIBILITY

InsuBuild 110T is compatible with all cements and most air-entraining agents meeting the ASTM standards.

The addition of **InsuBuild 110T** and **InsuAir 111** (air-entraining agent) to concrete is recommended where it is required to withstand freezing and thawing cycles.

PACKAGING

InsuBuild 110T is available in 1000 ltr bulk.

TYPICAL PROPERTIES

Colour:	Dark brown liquid
Specific gravity:	(1.190 ± 0.01) at 25° C
Chloride content:	Nil to BS 5075
Nitrate content:	Nil
pH:	5-7
Freezing point:	0°C;
Flashpoint:	N/A

STANDARDS

ASTM C- 494 Type B,D and G
BS 5075 Part 1 and 3

DOSAGE

Optimum dosage of **InsuBuild 110T** should be determined in trial mixes. As a guide, the following dosages are recommended as a starting point for any trial in normal concrete, a dosage of between 0.6% - 2.4% of cement weight. In high performance microsilica concrete.

Please consult Insumat's Technical Services Department for further information.

DISPENSING

InsuBuild 110T is a ready-to-use liquid, which is dispensed into the concrete together with mixing water.

The plasticising effect, or water reduction, is higher if the admixture is added to the concrete after 50-70% of the mixing water has been added. The addition of **InsuBuild 110T** to dry aggregate or cement is not recommended. Automatic dispensers are available in your local market.

InsuBuild 110T

High range, water reducing superplasticiser for producing free flowing concretes and promoting high early and ultimate strengths.

WORKABILITY

InsuBuild 110T ensures that free flowing concrete remains workable in excess of 3 hours at +20°C. Workability loss is dependent on temperature, on the type of cement, the nature of aggregates, the method of transport and initial workability. It is strongly recommended that concrete should be properly cured particularly in hot and dry climates.

STORAGE

InsuBuild 110T must be stored where temperatures do not drop below +5°C. If product has frozen, thaw and agitate until completely reconstituted. Store under cover, out of direct sunlight and protect from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice, consult Insumat Technical Services Department.

SHELF LIFE

Up to 24 months if stored according to manufacturer's instructions in unopened containers.

SAFETY PRECAUTIONS

InsuBuild 110T is not a fire or health hazard. Spillages should be washed down immediately with cold water. For further information, refer to the material safety data sheet.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information, contact Insumat's representative.

Insumat reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY STATEMENT

All products manufactured by Insumat Egypt, are manufactured to procedures certified to conform to the quality, environment, health & safety management systems described in the ISO 9001:2015, standard.

* Properties listed are based on laboratory controlled tests.

Actual measured data may vary due to circumstances beyond Insumat's control.

Manufacturing Insulating Materials and Products Company

Founded by
Osman Ahmed Osman
1974

☎ 011 1974 1974
📍 Plot 83 El Motawereen - El Sadat City - Menofia
✉ info@insumat.com
🌐 www.insumat.com